

RECLAIMED INSULATING OIL BS148:2009

L10B 7/4/2010

Application

Electrical Oil Services Ltd Reclaimed Insulating Oil is produced from selected used Insulating Oil, which is reprocessed to the requirements of British Standard Specification BS148:2009 and readily complies with all other user requirements.

PROPERTY	UNIT	TEST METHOD	SPECIFICATION	
			Min	Max
1. PHYSICAL				
Appearance		IEC 296	Clear, free from sediment	
Viscosity @ -15°C	cSt	ISO 3675		800
Viscosity @ 40°C	cSt	ISO 3675		13
Closed Flash Point	°C	EN 22719	135	
Pour Point	°C	BS 2000.15		-30
Density @ 20°C	Kg/dm ³	ISO 12185		0.895
2. CHEMICAL				
Neutralisation value	mgKOH/g	BS EN 6021-1		0.03
Corrosive Sulphur		BS EN 62535	Non corrosive	
Polycyclic Aromatics mass	%	BS2000 Part 346		3
PCB content	mg/kg	BS EN 61619		10
Water content Bulk Drums	mg/kg	BS EN 60814		20 30
Oxidation stability at 120°C 164h Acidity after Oxidation Sludge Value	mgKOH/g wt %	BS EN 61125 C		1.2 0.8
3. ELECTRICAL				
Dielectric Dissipation Factor @ 90°C		BS EN 60247		0.005
Breakdown Voltage	kV	BS EN 60156	30	

Health and Safety information sheets are available for all Electrical Oil Services Ltd products from the address below:

Electrical Oil Services Ltd, PO Box 79, Bridges Road, Stanlow Works, Ellesmere Port, Cheshire, CH65 4WD.

Orders/Enquiries - Telephone: (0845) 602 1003, Fax: (0845) 602 1004

All reasonable care has been taken to ensure that the information contained in this publication is accurate as at the date of printing. It should be noted however that the information above may be affected by changes occurring subsequent to the date of printing in the blend formulation or methods of application of any of the products referred to or in the requirements of any specification approval relating to any such products.